




Synthesis and Property Evaluations of Silicon Carbide Nanotube Reinforced Ceramic Matrix Composites

Dongming Zhu and Janet B. Hurst

Structures and Materials Division
NASA Glenn Research Center
Cleveland, Ohio 44135




**This work was supported by NASA Fundamental Aeronautics Program
Supersonics Project**

Materials Science & Technology 2011 Conference & Exhibition
October 16-20, 2011
Columbus, Ohio, USA



Motivation

- Environmental barrier coating (EBC) systems are critical for protecting Si-based ceramic hot-section components, e.g., SiC/SiC combustors and vanes
- Nanotube composites, potentially having high strength and functional properties, are currently being considered for environmental barrier coatings to improve the coating overall performance
- SiC nanotubes (SiCNTs) are being incorporated into EBC bond coats to help increase coating high temperature strength and toughness






Outline

- Synthesis of Silicon Carbide Nanotubes (SiCNT)
 - Process optimization
 - Nanotube annealing removing extra carbon
- Thermogravimetric Analysis (TGA) stability study in O₂ and air
- Nanotube Composite systems, HfO₂- and Yb₂Si₂O₇-based nanotube systems
 - Furnace phase stability testing of hot-processed composite systems
 - Strength comparisons
- Thermal Conductivity of HfO₂-Si, HfO₂-SiCNT and Yb₂Si₂O₇ systems
- Cyclic Durability of advanced coating-CMC systems
- Summary




Experimental

- SiC nanotubes synthesized by Si reaction with multiwall carbon nanotubes (CNTs, Pyrograf III® Carbon Fiber, HHT Grade) at 1400 °C in Ar + H₂
- Composite Materials/Specimens (hot-press) for property studies
 - 1" diameter x 2~3 mm thick disc SiCNT, composite specimens or coatings for HfO₂+Si and HfO₂+SiCNT, Yb₂Si₂O₇+Si, Yb₂Si₂O₇+SiCNT, and coated CMC specimens
- Thermogravimetric Analysis (TGA) in O₂ and Air, and furnace stability testing in air and
- X-ray diffraction and SEM characterizations
- Laser-heat-flux ball-on-ring test for mechanical property characterizations
- 3500 W continuous wave (cw) CO₂ laser (10.6 micron wavelength) used for high temperature thermal conductivity testing and high heat flux cyclic durability testing




SiCNT Processing and Process Optimization

- The SiCNT processing using Silicon + Carbon Nanotube (CNT) mixtures in $\text{Ar}+5\%\text{H}_2$ 1400 °C, with two 8 hr processing reaction cycles
- CNT vs. silicon weight ratios studied: 50:50, 55:45, 60:40, and 70:30 for environmental barrier coating composite applications






Laser Steady-State Heat Flux Thermal Conductivity Testing Approach



Schematic of the laser heat flux test principles







Laser Heat Flux Biaxial Strength Test Rig

Integrated high power CO₂ laser and mechanical Ring-on-Ring or Ball-on-Ring test rig



- Accommodates 1" diameter, or 2" diameter disc test specimens and also various configuration subelements
- Used for nanotube composite specimen fracture strength testing








SiCNT Processing and Process Optimization

- Optimized CNT/Si ratio found to be 55:45 with SiCNT content quality and nanotube morphology retention
- Obtained almost full β -SiC phase for the SiCNT based on X-ray diffraction analysis







Less Optimized SiCNTs Showing Larger Amount of Either Incomplete CNT Conversion or Damaged Nanotubes






The HfO_2 +Si Bond Coats Showed Significantly Improved Temperature Capability as Compared to Si bond Coats


- Higher stability observed even after 1450°C+ temperature testing



Cross-section, Hot-pressed HfO_2 -50wt%Si on CMC, 1350°C tested




Cross-section, EB-PVD HfO_2 -Si, 1500°C tested




The HfO_2 +SiCNT(Si) Bond Coats Showed High Temperature Stability in Oxidizing Environments


- HfO_2 , SiCNT and HfO_2 silicate are major phases after the 100hr testing up to 1450 °C
- Further stability improvements can be achieved in the nanotube composite systems by alloying approaches



SiC nanotube (SiCNT) and HfO_2 -based nanotube composite coatings





X-ray diffraction analysis



Yb-Doped SiCNTs Processed to Improve the Nanotube and Composite Stability


- Ytterbium alloying by SiCNT reacting with fine Yb_2O_3 powders in $\text{Ar}+\text{H}_2$
- EDS and X-ray Analysis used to confirm the Yb incorporation of the SiCNTs






Strength Improvements in the Nanotubes and Banotube Composite Systems

- Annealing and Si addition improved the SiCNT strength
- 2 ~ 3 X improvements were observed compared to the baselines
- Further stability and strength improvements may be achieved with more sophisticated, high toughness systems, such as with t' HfO₂/ZrO₂



Biaxial bend strength, MPa






Biaxial bend strength, MPa



Oxidation Kinetics of SiCNTs




- Silica scale growth on SiCNTs follows pseudo-parabolic behavior
- Upper temperature limit found $\sim 1100^\circ\text{C}$ in O_2 environment
- Slower oxidation rate observed in air as compared to oxygen environment tests
- Effective protection barrier layer expected to improve the SiCNT composite stability
- Activation energy determined and good agreement between TGA and scale thickness measurement results






SiCNTs Stability in Protective Coatings




- SiCNTs survived in furnace testing at 1300 °C for 50 hours






Thermal Conductivity of HfO_2 -Si Systems


- Thermal conductivity maintained stable after high temperature 100 hr annealing






Thermal Conductivity of HfO_2 -12.4wt%SiCNT



- Relatively low thermal conductivity, possibly due to high interface areas and interface phase thermal resistance
- Effect of nanotube fractions on thermal conductivity is being evaluated and modeled






Thermal Conductivity of $\text{Yb}_2\text{Si}_2\text{O}_7$ -50wt%SiCNT


- Slightly enhanced thermal conductivity at high temperature as compared to the bulk $\text{Yb}_2\text{Si}_2\text{O}_7$ due to the SiCNT addition





High Heat Flux Thermal Gradient Cyclic Durability Evaluation of Environmental Barrier Coating and Bond Coat Systems

- Laser high heat flux rig thermal gradient thermal cyclic testing at surface temperature of 1482°C (2700°F)
- Advanced bond coats tested at up to 1375°C



HfO₂-yttria silicate coating with
HfO₂-Si and HfO₂-Si/SiCNT bond
coat, after 100hr testing at T_{surface}
1482°C/T_{interface} 1375°C



Summary

- SiCNT processing has been optimized for EBC bond coat applications, with the optimum Si:CNT weight ratio being 55:45.
- SiCNT annealing or purification treatment improved strength by removing residual carbon
- Composite HfO_2 -SiCNT-Si and $\text{Yb}_2\text{Si}_2\text{O}_7$ -SiCNT-Si bond coats synthesized for high temperature environmental barrier coating applications, showed significantly improved strength and high temperature stability
- SiCNT demonstrated the strength and further enhanced with alloy doping systems
- Thermal conductivity of HfO_2 +SiCNT and $\text{Yb}_2\text{Si}_2\text{O}_7$ +SiCNT bond coats evaluated
- Advanced alloyed nanotubes were synthesized for more advanced system applications



Summary

The work was supported by NASA Fundamental Aeronautics Program, Supersonics Project.

The authors would like to acknowledge the contributions from the following:

- Samantha Benkel, Nadia Ahlborg, and Rachel Guarriello (NASA Intern Students)
- Dr. Rick Rogers (NASA GRC, X-ray Diffraction)
- Terry McCue (ASRC/NASA GRC, SEM/EDS)

The authors are grateful to Robert Angus of NASA Glenn Research Center for processing the nano-tube specimens.